

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C22C 38/44, 38/50	A1	(11) International Publication Number: WO 97/12073 (43) International Publication Date: 3 April 1997 (03.04.97)
(21) International Application Number: PCT/US96/14214 (22) International Filing Date: 5 September 1996 (05.09.96) (30) Priority Data: 08/533,159 25 September 1995 (25.09.95) US (71) Applicant: CRS HOLDINGS, INC. [US/US]; 209F Baynard Building, 3411 Silverside Road, Wilmington, DE 19810 (US). (72) Inventors: MARTIN, James, W.; 11 Marie Drive, Sinking Spring, PA 19603 (US). KOSA, Theodore; 171 Oakmont Court, Reading, PA 19607 (US). DULMAINE, Bradford, A.; 4105 Kinder Drive, Muhlenberg, PA 19605 (US). (74) Agents: BRUSTEIN, Mitchell, R. et al.; Dann, Dorfman, Herrell and Skillman, P.C., Suite 720, 1601 Market Street, Philadelphia, PA 19103-2307 (US).		(81) Designated States: BR, CA, IL, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: HIGH-STRENGTH, NOTCH-DUCTILE PRECIPITATION-HARDENING STAINLESS STEEL ALLOY (57) Abstract A precipitation hardenable, martensitic stainless steel alloy is disclosed consisting essentially of, in weight percent, about C 0.03 max, Mn 1.0 max, Si 0.75 max, P 0.040 max, S 0.020 max, Cr 10 - 13, Ni 10.5 - 11.6, Ti 1.5 - 1.8, Mo 0.25 - 1.5, Cu 0.95 max, Al 0.25 max, Nb 0.3 max, B 0.10 max, N 0.030 max, the balance essentially iron. The disclosed alloy provides a unique combination of stress-corrosion cracking resistance, strength, and notch toughness.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

**High-Strength, Notch-Ductil Precipitation-Hardening
Stainless Steel Alloy**

Field of the Invention

The present invention relates to precipitation hardenable, martensitic stainless steel alloys and in particular to a Cr-Ni-Ti-Mo martensitic stainless steel alloy, and an article made therefrom, having a unique combination of stress-corrosion cracking resistance, strength, and notch toughness.

Background of the Invention

Many industrial applications, including the aircraft industry, require the use of parts manufactured from high strength alloys. One approach to the production of such high strength alloys has been to develop precipitation hardening alloys. A precipitation hardening alloy is an alloy wherein a precipitate is formed within the ductile matrix of the alloy. The precipitate particles inhibit dislocations within the ductile matrix thereby strengthening the alloy.

One of the known age hardening stainless steel alloys seeks to provide high strength by the addition of titanium and columbium and by controlling chromium, nickel, and copper to ensure a martensitic structure. To provide optimum toughness, this alloy is annealed at a relatively low temperature. Such a low annealing temperature is required to form an Fe-Ti-Cb rich Laves phase prior to aging. Such action prevents the excessive formation of hardening precipitates and provides greater availability of nickel for austenite reversion. However, at the low annealing temperatures used for this alloy, the microstructure of the alloy does not fully recrystallize. These conditions do not promote effective use of hardening element additions

- 2 -

and produce a material whose strength and toughness are highly sensitive to processing.

In another known precipitation hardenable stainless steel the elements chromium, nickel,
5 aluminum, carbon, and molybdenum are critically balanced in the alloy. In addition, manganese, silicon, phosphorus, sulfur, and nitrogen are maintained at low levels in order not to detract from the desired combination of properties provided by the
10 alloy.

While the known precipitation hardenable, stainless steels have hitherto provided acceptable properties, a need has arisen for an alloy that provides better strength together with at least the
15 same level of notch toughness and corrosion resistance provided by the known precipitation hardenable, stainless steels. An alloy having higher strength while maintaining the same level of notch toughness and corrosion resistance, particularly resistance to
20 stress corrosion cracking, would be particularly useful in the aircraft industry because structural members fabricated from such alloys could be lighter in weight than the same parts manufactured from currently available alloys. A reduction in the weight
25 of such structural members is desirable since it results in improved fuel efficiency.

Given the foregoing, it would be highly desirable to have an alloy which provides an improved combination of stress-corrosion resistance, strength,
30 and notch toughness while being easily and reliably processed.

Summary of the Invention

The shortcomings associated with the known
35 precipitation hardenable, martensitic stainless steel alloys are solved to a large degree by the alloy in accordance with the present invention. The alloy

- 3 -

according to the present invention is a precipitation
hardening Cr-Ni-Ti-Mo martensitic stainless steel
alloy that provides a unique combination of stress-
corrosion cracking resistance, strength, and notch
5 toughness.

The broad, intermediate, and preferred
compositional ranges of the precipitation hardening,
martensitic stainless steel of the present invention
are as follows, in weight percent:

10

	<u>Broad</u>	<u>Intermediate</u>	<u>Preferred</u>
C	0.03 max	0.02 max	0.015 max
Mn	1.0 max	0.25 max	0.10 max
15 Si	0.75 max	0.25 max	0.10 max
P	0.040 max	0.015 max	0.010 max
S	0.020 max	0.010 max	0.005 max
Cr	10 - 13	10.5 - 12.5	11.0 - 12.0
Ni	10.5 - 11.6	10.75 - 11.25	10.85 - 11.25
20 Ti	1.5 - 1.8	1.5 - 1.7	1.5 - 1.7
Mo	0.25 - 1.5	0.75 - 1.25	0.9 - 1.1
Cu	0.95 max	0.50 max	0.25 max
Al	0.25 max	0.050 max	0.025 max
Nb	0.3 max	0.050 max	0.025 max
25 B	0.010 max	0.001 - 0.005	0.0015 - 0.0035
N	0.030 max	0.015 max	0.010 max

The balance of the alloy is essentially iron
30 except for the usual impurities found in commercial
grades of such steels and minor amounts of additional
elements which may vary from a few thousandths of a
percent up to larger amounts that do not objectionably
detract from the desired combination of properties
35 provided by this alloy.

The foregoing tabulation is provided as a
convenient summary and is not intended thereby to
restrict the lower and upper values of the ranges of
the individual elements of the alloy of this invention
40 for use in combination with each other, or to restrict
the ranges of the elements for use solely in
combination with each other. Thus, one or more of the

- 4 -

element ranges of the broad composition can be used with one or more of the other ranges for the remaining elements in the preferred composition. In addition, a minimum or maximum for an element of one preferred embodiment can be used with the maximum or minimum for that element from another preferred embodiment. Throughout this application, unless otherwise indicated, percent (%) means percent by weight.

10 Detailed Description

 In the alloy according to the present invention, the unique combination of strength, notch toughness, and stress-corrosion cracking resistance is achieved by balancing the elements chromium, nickel, titanium, and molybdenum. At least about 10%, better yet at least about 10.5%, and preferably at least about 11.0% chromium is present in the alloy to provide corrosion resistance commensurate with that of a conventional stainless steel under oxidizing conditions. At least about 10.5%, better yet at least about 10.75%, and preferably at least about 10.85% nickel is present in the alloy because it benefits the notch toughness of the alloy. At least about 1.5% titanium is present in the alloy to benefit the strength of the alloy through the precipitation of a nickel-titanium-rich phase during aging. At least about 0.25%, better yet at least about 0.75%, and preferably at least about 0.9% molybdenum is also present in the alloy because it contributes to the alloy's notch toughness.

30 Molybdenum also benefits the alloy's corrosion resistance in reducing media and in environments which promote pitting attack and stress-corrosion cracking.

 When chromium, nickel, titanium, and/or molybdenum are not properly balanced, the alloy's ability to transform fully to a martensitic structure using conventional processing techniques is inhibited. Furthermore, the alloy's ability to remain

- 5 -

substantially fully martensitic when solution treated and age-hardened is impaired. Under such conditions the strength provided by the alloy is significantly reduced. Therefore, chromium, nickel, titanium, and molybdenum present in this alloy are restricted. More particularly, chromium is limited to not more than about 13%, better yet to not more than about 12.5%, and preferably to not more than about 12.0% and nickel is limited to not more than about 11.6% and preferably to not more than about 11.25%. Titanium is restricted to not more than about 1.8% and preferably to not more than about 1.7% and molybdenum is restricted to not more than about 1.5%, better yet to not more than about 1.25%, and preferably to not more than about 1.1%.

Additional elements such as boron, aluminum, niobium, manganese, and silicon may be present in controlled amounts to benefit other desirable properties provided by this alloy. More specifically, up to about 0.010% boron, better yet up to about 0.005%, and preferably up to about 0.0035% boron can be present in the alloy to benefit the hot workability of the alloy. In order to provide the desired effect, at least about 0.001% and preferably at least about 0.0015% boron is present in the alloy.

Aluminum and/or niobium can be present in the alloy to benefit the yield and ultimate tensile strengths. More particularly, up to about 0.25%, better yet up to about 0.10%, still better up to about 0.050%, and preferably up to about 0.025% aluminum can be present in the alloy. Also, up to about 0.3%, better yet up to about 0.10%, still better up to about 0.050%, and preferably up to about 0.025% niobium can be present in the alloy. Although higher yield and ultimate tensile strengths are obtainable when aluminum and/or niobium are present in this alloy, the increased strength is developed at the expense of

- 6 -

notch toughness. Therefore, when optimum notch toughness is desired, aluminum and niobium are restricted to the usual residual levels.

Up to about 1.0%, better yet up to about 0.5%,
5 still better up to about 0.25%, and preferably up to about 0.10% manganese and/or up to about 0.75%, better yet up to about 0.5%, still better up to about 0.25%, and preferably up to about 0.10% silicon can be present in the alloy as residuals from scrap sources
10 or deoxidizing additions. Such additions are beneficial when the alloy is not vacuum melted. Manganese and/or silicon are preferably kept at low levels because of their deleterious effects on toughness, corrosion resistance, and the austenite-martensite phase balance in the matrix material.
15

The balance of the alloy is essentially iron apart from the usual impurities found in commercial grades of alloys intended for similar service or use. The levels of such elements are controlled so as not to adversely affect the desired properties.
20

In particular, too much carbon and/or nitrogen impair the corrosion resistance and deleteriously affect the toughness provided by this alloy. Accordingly, not more than about 0.03%, better yet not
25 more than about 0.02%, and preferably not more than about 0.015% carbon is present in the alloy. Also, not more than about 0.030%, better yet not more than about 0.015%, and preferably not more than about 0.010% nitrogen is present in the alloy. When carbon
30 and/or nitrogen are present in larger amounts, the carbon and/or nitrogen bonds with titanium to form titanium-rich non-metallic inclusions. That reaction inhibits the formation of the nickel-titanium-rich phase which is a primary factor in the high strength provided by this alloy.
35

Phosphorus is maintained at a low level because of its deleterious effect on toughness and corrosion

- 7 -

resistance. Accordingly, not more than about 0.040%, better yet not more than about 0.015%, and preferably not more than about 0.010% phosphorus is present in the alloy.

5 Not more than about 0.020%, better yet not more than about 0.010%, and preferably not more than about 0.005% sulfur is present in the alloy. Larger amounts of sulfur promote the formation of titanium-rich non-metallic inclusions which, like carbon and nitrogen,
10 inhibit the desired strengthening effect of the titanium. Also, greater amounts of sulfur deleteriously affect the hot workability and corrosion resistance of this alloy and impair its toughness, particularly in a transverse direction.

15 Too much copper deleteriously affects the notch toughness, ductility, and strength of this alloy. Therefore, the alloy contains not more than about 0.95%, better yet not more than about 0.75%, still better not more than about 0.50%, and preferably not
20 more than about 0.25% copper.

No special techniques are required in melting, casting, or working the alloy of the present invention. Vacuum induction melting or vacuum
25 induction melting followed by vacuum arc remelting are the preferred methods of melting and refining, but other practices can be used. In addition, this alloy can be made using powder metallurgy techniques, if desired. Further, although the alloy of the present invention can be hot or cold worked, cold working
30 enhances the mechanical strength of the alloy.

The precipitation hardening alloy of the present invention is solution annealed to develop the desired combination of properties. The solution annealing temperature should be high enough to dissolve
35 essentially all of the undesired precipitates into the alloy matrix material. However, if the solution annealing temperature is too high, it will impair the

- 8 -

fracture toughness of the alloy by promoting excessive grain growth. Typically, the alloy of the present invention is solution annealed at 1700 °F - 1900 °F (927 °C - 1038 °C) for 1 hour and then quenched.

5 When desired, this alloy can also be subjected to a deep chill treatment after it is quenched, to further develop the high strength of the alloy. The deep chill treatment cools the alloy to a temperature sufficiently below the martensite finish temperature
10 to ensure the completion of the martensite transformation. Typically, a deep chill treatment consists of cooling the alloy to below about -100°F (-73°C) for about 1 hour. However, the need for a deep chill treatment will be affected, at least in
15 part, by the martensite finish temperature of the alloy. If the martensite finish temperature is sufficiently high, the transformation to a martensitic structure will proceed without the need for a deep chill treatment. In addition, the need for a deep
20 chill treatment may also depend on the size of the piece being manufactured. As the size of the piece increases, segregation in the alloy becomes more significant and the use of a deep chill treatment becomes more beneficial. Further, the length of time
25 that the piece is chilled may need to be increased for large pieces in order to complete the transformation to martensite.

 The alloy of the present invention is age hardened in accordance with techniques used for the known
30 precipitation hardening, stainless steel alloys, as are known to those skilled in the art. For example, the alloys are aged at a temperature between about 900 °F (482 °C) and about 1150 °F (621 °C) for about 4 hours. The specific aging conditions used are
35 selected by considering that: (1) the ultimate tensile strength of the alloy decreases as the aging temperature increases; and (2) the time required to

- 9 -

age harden the alloy to a desired strength level increases as the aging temperature decreases.

The alloy of the present invention can be formed into a variety of product shapes for a wide variety of uses and lends itself to the formation of billets, bars, rod, wire, strip, plate, or sheet using conventional practices. The alloy of the present invention is useful in a wide range of practical applications which require an alloy having a good combination of stress-corrosion cracking resistance, strength, and notch toughness. In particular, the alloy of the present invention can be used to produce structural members and fasteners for aircraft and the alloy is also well suited for use in medical or dental instruments.

- 10 -

Table 1

Ex./Ht. No.	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Ti	B	N	Nb	Al	Fe
1	0.003	0.09	0.02	0.006	0.003	11.54	11.13	1.00	0.05	1.61	0.0013	0.004	<0.01	---	Bal.
2	0.006	0.08	0.05	0.008	0.005	11.57	11.02	1.00	0.05	1.52	0.0019	0.004	<0.01	<0.01	Bal.
3	0.009	0.08	0.04	0.008	0.004	11.61	11.03	1.00	0.06	1.68	0.0021	0.005	<0.01	<0.01	Bal.
4	0.008	0.08	0.05	0.007	0.004	11.60	11.05	1.43	0.05	1.52	0.0020	0.005	<0.01	<0.01	Bal.
5	0.012	0.08	0.07	0.010	0.001	11.58	10.46	1.00	0.06	1.58	0.0024	0.004	<0.01	<0.01	Bal.
6	0.008	0.10	0.07	0.009	0.003	11.54	10.77	1.00	0.05	1.55	0.0020	0.004	<0.01	<0.01	Bal.
7	0.008	0.10	0.05	0.009	0.002	11.62	11.05	0.99	0.07	1.58	0.0030	0.003	<0.01	0.017	Bal. ¹
8	0.007	0.07	0.06	0.010	0.001	11.63	10.92	0.75	0.06	1.58	0.0024	0.004	<0.01	<0.01	Bal.
9	0.003	0.08	0.07	0.009	0.001	11.49	10.84	0.50	0.06	1.58	0.0023	0.004	<0.01	<0.01	Bal.
10	0.012	0.08	0.07	0.009	0.002	11.60	10.84	0.28	0.06	1.50	0.0025	0.002	<0.01	0.01	Bal.
11	0.007	0.10	0.05	0.010	0.001	11.62	10.99	1.49	0.06	1.67	0.0020	0.004	<0.01	0.014	Bal. ²
12	0.006	0.08	0.05	0.007	0.005	11.58	11.08	0.98	0.05	1.52	0.0017	0.005	0.26	<0.01	Bal.
13	0.007	0.08	0.05	0.007	0.005	11.56	10.98	1.00	0.05	1.70	0.0016	0.004	0.25	<0.01	Bal.
14	0.006	0.08	0.05	0.007	0.005	11.55	11.02	1.02	0.05	1.54	0.0018	0.005	<0.01	0.22	Bal.
15	0.008	0.08	0.04	0.007	0.005	11.62	11.03	1.03	0.05	1.54	0.0017	0.005	0.25	0.20	Bal.
16	0.007	0.08	0.04	0.008	0.005	11.68	11.09	1.47	0.05	1.52	0.0017	0.004	0.26	<0.01	Bal.
17	0.008	0.08	0.05	0.006	0.003	11.56	10.98	1.00	0.92	1.49	0.0020	0.004	0.25	<0.01	Bal.
18	0.009	0.08	0.04	0.005	0.005	11.60	11.05	1.01	0.92	1.52	0.0024	0.004	<0.01	<0.01	Bal.
A	0.030	0.02	0.02	0.004	0.006	12.63	8.17	2.13	0.03	0.01	<0.0010	0.006	<0.01	1.10	Bal.
B	0.035	0.06	0.06	0.002	0.003	12.61	8.20	2.14	0.06	0.016	<0.0010	0.003	<0.01	1.14	Bal.
C	0.007	0.08	0.04	0.008	0.003	11.66	8.61	0.11	2.01	1.10	0.0022	0.005	0.25	<0.01	Bal.
D	0.006	0.08	0.05	0.004	0.002	11.58	8.29	0.09	2.14	1.18	0.0028	0.005	0.24	0.022	Bal. ¹

¹ Also contains 0.002% zirconium² Also contains <0.002% zirconium

- 11 -

Examples

In order to demonstrate the unique combination of properties provided by the present alloy, Examples 1-18 of the alloy of the present invention having the compositions in weight percent shown in Table 1 were prepared. For comparison purposes, Comparative Heats A-D with compositions outside the range of the present invention were also prepared. Their weight percent compositions are also included in Table 1.

Alloys A and B are representative of one of the known precipitation hardening, stainless steel alloys and Alloys C and D are representative of another known precipitation hardening, stainless steel alloy.

Example 1 was prepared as a 17 lb. (7.7 kg) laboratory heat which was vacuum induction melted and cast as a 2.75 inch (6.98 cm) tapered square ingot. The ingot was heated to 1900 °F (1038 °C) and press-forged to a 1.375 inch (3.49 cm) square bar. The bar was finish-forged to a 1.125 inch (2.86 cm) square bar and air-cooled to room temperature. The forged bar was hot rolled at 1850 °F (1010 °C) to a 0.625 inch (1.59 cm) round bar and then air-cooled to room temperature.

Examples 2-4 and 12-18, and Comparative Heats A and C were prepared as 25 lb. (11.3 kg) laboratory heats which were vacuum induction melted under a partial pressure of argon gas and cast as 3.5 inch (8.9 cm) tapered square ingots. The ingots were press-forged from a starting temperature of 1850 °F (1010 °C) to 1.875 inch (4.76 cm) square bars which were then air-cooled to room temperature. The square bars were reheated, press-forged from the temperature of 1850 °F (1010 °C) to 1.25 inch (3.18 cm) square bars, reheated, hot-rolled from the temperature of 1850 °F (1010 °C) to 0.625 inch (1.59 cm) round bars, and then air-cooled to room temperature.

- 12 -

Examples 5, 6, and 8-10 were prepared as 37 lb. (16.8 kg) laboratory heats which were vacuum induction melted under a partial pressure of argon gas and cast as 4 inch (10.2 cm) tapered square ingots. The ingots were press-forged from a starting temperature of 1850 °F (1010 °C) to 2 inch (5.1 cm) square bars and then air-cooled. A length was cut from each 2 inch (5.1 cm) square forged bar and forged from a temperature of 1850 °F (1010 °C) to 1.31 inch (3.33 cm) square bar. The forged bars were hot rolled at 1850°F (1010°C) to 0.625 inch (1.59 cm) round bars and air cooled to room temperature.

Examples 7 and 11, and Comparative Heats B and D were prepared as 125 lb. (56.7 kg) laboratory heats which were vacuum induction melted under a partial pressure of argon gas and cast as 4.5 inch (11.4 cm) tapered square ingots. The ingots were press-forged from a starting temperature of 1850 °F (1010 °C) to 2 inch (5.1 cm) square bars and then air-cooled to room temperature. The bars were reheated and then forged from a temperature of 1850 °F (1010 °C) to 1.31 inch (3.33 cm) square bars. The forged bars were hot rolled at 1850°F (1010°C) to 0.625 inch (1.59 cm) round bars and air cooled to room temperature.

The bars of each Example and Comparative Heat were rough turned in the annealed/cold treated condition to produce smooth tensile, stress-corrosion, and notched tensile specimens having the dimensions indicated in Table 2. Each specimen was cylindrical with the center of each specimen being reduced in diameter with a minimum radius connecting the center section to each end section of the specimen. The stress-corrosion specimens were polished to a nominal gage diameter with a 400 grit surface finish.

35

- 13 -

Table 2

Center Section

Specimen Type	Length in./cm	Diameter in./cm	Length in./cm	Diameter in./cm	Minimum radius in./cm	Gage diameter in. (cm)
Smooth tensile	3.5/8.9	0.5/1.27	1.0/2.54	0.25/0.64	0.1875/0.476	---
Stress-corrosion	5.5/14.0	0.436/1.11	1.0/2.54	0.25/0.64	0.25/0.64	0.225/0.57
Notched tensile ⁽¹⁾	3.75/9.5	0.50/1.27	1.75/4.4	0.375/0.95	0.1875/0.476	---

⁽¹⁾ A notch was provided around the center of each notched tensile specimen. The specimen diameter was 0.252 in. (0.64 cm) at the base of the notch; the notch root radius was 0.0010 inches (0.0025 cm) to produce a stress concentration factor (K_t) of 10.

The test specimens of each Ex./Ht. were heat treated in accordance with Table 3 below. The heat treatment conditions used were selected to provide peak strength.

Table 3

	<u>Solution Treatment</u>	<u>Aging Treatment</u>
Exs. 1-18	1800°F(982°C)/1 hour/WQ ^{1,2}	900°F(482°C)/4 hours/AC ³
Hts. A and B	1700°F(927°C)/1 hour/WQ ⁴	950°F(510°C)/4 hours/AC
Hts. C and D	1500°F(816°C)/1 hour/WQ	900°F(482°C)/4 hours/AC

¹ WQ= water quenched.

² Cold treated at -100°F (-73°C) for 1 hour then warmed in air.

³ AC= air cooled.

⁴ Cold treated at 33°F (0.6°C) for 1 hour then warmed in air.

The mechanical properties of Examples 1-18 were compared with the properties of Comparative Heats A-D. The properties measured include the 0.2% yield strength (0.2% YS), the ultimate tensile strength (UTS), the percent elongation in four diameters (% Elong.), the percent reduction in area (% Red.), and the notch tensile strength (NTS). All of the properties were measured along the longitudinal direction. The results of the measurements are given in Table 4.

Table 4

Ex./Ht. No.	Cr	Ni	Mo	Ti	.2% YS (ksi/MPa)	UTS (ksi/MPa)	% Elong.	% Red. in Area	NTS (ksi/MPa)	NTS/UTS
1	11.54	11.13	1.00	1.61	253.7/1749	264.3/1822	12.0	50.5	309.0/2130*	1.17
2	11.57	11.02	1.00	1.52	244.7/1687	256.2/1766	14.7	53.5	341.2/2352*	1.33
3	11.61	11.03	1.00	1.68	246.8/1702	260.1/1793	12.6	49.4	324.9/2240*	1.25
4	11.60	11.05	1.43	1.52	244.2/1684	256.7/1770	14.4	58.8	352.5/2430*	1.37
5	11.58	10.46	1.00	1.58	248.5/1713*	266.0/1834*	11.5*	49.6*	288.3/1988*	1.08
6	11.54	10.77	1.00	1.55	251.5/1734*	268.3/1850*	11.7*	51.7*	324.9/2240*	1.21
7	11.62	11.05	0.99	1.58	240.5/1658*	261.6/1804*	11.5*	51.1*	344.5/2375*	1.32
8	11.63	10.92	0.75	1.58	250.4/1726*	267.9/1847*	12.4*	54.5*	361.4/2492*	1.35
9	11.49	10.84	0.50	1.58	251.4/1733*	267.9/1847*	11.3*	50.6*	339.3/2339*	1.27
10	11.60	10.84	0.28	1.50	248.4/1713*	264.5/1824*	12.1*	57.0*	347.3/2395*	1.31
11	11.62	10.99	1.49	1.67	227.6/1569*	255.6/1762*	11.6*	47.9*	332.8/2295*	1.30
12	11.58	11.08	0.98	1.52	250.7/1728	262.4/1809	12.2	52.4	312.2/2153*	1.19
13	11.56	10.98	1.00	1.70	255.8/1764	270.2/1863	13.2	50.2	281.6/1942*	1.04
14	11.55	11.02	1.02	1.54	248.7/1714	262.9/1813	13.9	50.7	262.2/1808*	1.00
15	11.62	11.03	1.03	1.54	247.8/1708	262.4/1809	12.4	48.3	289.3/1995*	1.10
16	11.68	11.09	1.47	1.52	238.3/1643	251.2/1732	15.9	56.0	318.6/2197*	1.27
17	11.56	10.98	1.00	1.49	239.2/1649	254.6/1755	12.7	39.6	289.0/1993*	1.14
18	11.60	11.05	1.01	1.51	235.3/1622	250.0/1724	11.8	42.4	311.9/2150*	1.25
A	12.63	8.17	2.13	0.01	210.1/1449	224.4/1547	14.4	59.4	346.9/2392*	1.54
B	12.61	8.20	2.14	0.016	209.2/1442	230.1/1586	15.9	65.4	349.8/2412	1.52
C	11.66	8.61	0.11	1.10	250.5/1727	254.3/1753	12.2	52.0	319.6/2204*	1.26
D	11.58	8.29	0.09	1.18	251.0/1731	259.3/1788	10.7	46.7	329.7/2273	1.27

* The value reported is an average of two measurements.

- 15 -

The data in Table 4 show that Examples 1-18 of the present invention provide superior yield and tensile strength compared to Heats A and B, while providing acceptable levels of notch toughness, as indicated by the NTS/UTS ratio, and ductility. Thus, it is seen that Examples 1-18 provide a superior combination of strength and ductility relative to Heats A and B.

Moreover, the data in Table 4 also show that Examples 1-18 of the present invention provide tensile strength that is at least as good as to significantly better than Heats C and D, while providing acceptable yield strength and ductility, as well as an acceptable level of notch toughness as indicated by the NTS/UTS ratio.

The stress-corrosion cracking resistance properties of Examples 7-11 in a chloride-containing medium were compared to those of Comparative Heats B and D via slow-strain-rate testing. For the stress-corrosion cracking test, the specimens of Examples 7-11 were solution treated similarly to the tensile specimens and then over-aged at a temperature selected to provide a high level of strength. The specimens of Comparative Heats B and D were solution treated similarly to their respective tensile specimens, but over-aged at a temperature selected to provide the level of stress-corrosion cracking resistance typically specified in the aircraft industry. More specifically, Examples 7-11 were age hardened at 1000°F (538°C) for 4 hours and then air-cooled and Comparative Heats B and D were age hardened at 1050°F (566 °C) for 4 hours and then air-cooled.

The resistance to stress-corrosion cracking was tested by subjecting sets of the specimens of each example/heat to a tensile stress by means of a constant extension rate of 4×10^{-6} inches/sec (1×10^{-5} cm/sec). Tests were conducted in each of four different media: (1) a boiling solution of 10.0%

- 16 -

NaCl acidified to pH 1.5 with H_3PO_4 ; (2) a boiling solution of 3.5% NaCl at its natural pH (4.9 - 5.9); (3) a boiling solution of 3.5% NaCl acidified to pH 1.5 with H_3PO_4 ; and (4) air at 77 °F (25 °C). The tests conducted in air were used as a reference against which the results obtained in the chloride-containing media could be compared.

The results of the stress-corrosion testing are given in Table 5 including the time-to-fracture of the test specimen (Total Test Time) in hours, the percent elongation (% Elong.), and the reduction in cross-sectional area (% Red. in Area).

Table 5

Ex./Ht. No.	Environment	Total Test Time (hrs)	% Elong.	% Red. in Area
7	Boiling 10.0% NaCl at pH 1.5	8.5	4.9	21.5
20	Boiling 3.5% NaCl at pH 1.5	9.4	5.4	25.0
	"	13.5	11.3	53.7
	"	13.6	11.1	58.6
	"	12.6	11.5	53.9
	Boiling 3.5% NaCl at pH 5.8	14.4	12.0	62.0
25	"	13.8	11.7	60.2
	Air at 77°F (25°C)	14.4	12.6	60.4
	"	12.6	10.6	58.6
	"	14.2	12.8	56.1
8	Boiling 10.0% NaCl at pH 1.5	8.2	5.4	23.8
30	Boiling 3.5% NaCl at pH 1.5	8.3	5.3	21.4
	"	13.0	11.0	54.4
	"	13.3	11.0	53.4
	Boiling 3.5% NaCl at pH 5.9	13.9	13.8	64.8
	"	14.1	13.8	64.1
35	Air at 77°F (25°C)	14.0	13.4	62.4
	"	14.6	14.3	63.7
	"	14.0	13.6	63.2
9	Boiling 10.0% NaCl at pH 1.5	10.0	6.6	20.6
	"	10.3	6.2	20.7
40	Boiling 3.5% NaCl at pH 1.5	12.6	10.6	50.1
	"	12.8	12.0	49.5
	Boiling 3.5% NaCl at pH 4.9	13.6	12.2	55.8
	"	13.6	12.0	54.4
	Air at 77°F (25°C)	13.8	12.6	59.6
45	"	14.0	12.8	58.5
10	Boiling 10.0% NaCl at pH 1.5	9.6	7.0	27.9
	"	10.4	7.7	17.9
	Boiling 3.5% NaCl at pH 1.5	13.7	11.8	58.1
	"	13.8	11.5	54.0
50	Boiling 3.5% NaCl at pH 5.9	13.5	13.3	61.8
	"	14.3	14.6	61.7
	"	14.0	11.9	52.8
	Air at 77°F (25°C)	14.4	13.1	63.8
	"	14.4	12.7	63.9
55	11 Boiling 10.0% NaCl at pH 1.5	9.5	6.5	20.8
	"	9.5	5.0	22.2
	"	11.3	7.2	22.9
	Boiling 3.5% NaCl at pH 1.5	13.5	10.8	58.6
	"	13.9	11.0	56.5
	"	13.0	11.6	53.2
60	Boiling 3.5% NaCl at pH 5.8	14.6	12.3	62.8
	"	14.1	12.7	61.6
	Air at 77°F (25°C)	14.4	12.7	61.5
	"	13.4	11.5	58.5
	"	13.6	11.3	53.8
65	B Boiling 10.0% NaCl at pH 1.5	14.9	14.5	51.7
	"	15.2	16.6	65.2
	"	13.7	12.9	59.8
	Boiling 3.5% NaCl at pH 1.5	14.2	13.3	69.9
	"	13.5	14.0	69.9
70	"	13.8	14.5	68.4
	Boiling 3.5% NaCl at pH 5.8	13.4	13.9	66.1

- 17 -

		*	13.6	13.3	67.6
		Air at 77°F (25°C)	14.1	15.1	69.9
		"	15.1	15.7	69.7
		"	15.4	15.4	69.3
5	D	Boiling 10.0% NaCl at pH 1.5	7.4	3.7	6.9
		"	9.6	8.3	15.6
		"	10.2	10.0	19.2
		Boiling 3.5% NaCl at pH 1.5	13.4	11.3	49.6
		"	13.2	10.1	46.1
10		"	12.8	10.7	44.5
		Boiling 3.5% NaCl at pH 5.8	13.4	11.5	51.3
		"	13.4	11.9	52.0
		Air at 77°F (25°C)	14.1	15.2	56.0
		"	15.1	14.4	54.4
15		"	15.8	15.4	59.6

" These measurements represent the reference values for the boiling 10.0% NaCl test conditions only.

The relative stress-corrosion cracking resistance of the tested alloys can be better understood by reference to a ratio of the measured parameter in the corrosive medium to the measured parameter in the reference medium. Table 6 summarizes the data of Table 5 by presenting the data in a ratio format for ease of comparison. The values in the column labeled "TC/TR" are the ratios of the average time-to-fracture under the corrosive condition to the average time-to-fracture under the reference condition. The values in the column labeled "EC/ER" are the ratios of the average % elongation under the indicated corrosive condition to the average % elongation under the reference condition. Likewise, the values in the column labeled "RC/RR" are the ratios of the average % reduction in area under the indicated corrosive condition to the average % reduction in area under the reference condition.

Table 6

Ex./Ht.	No.	TC/TR ⁽¹⁾	EC/ER ⁽²⁾	RC/RR ⁽³⁾
5	(Boiling 10.0% NaCl at pH 1.5)			
	7	.67	.44	.41
	8	.58	.38	.36
10	9	.73	.50	.35
	10	.69	.57	.36
	11	.75	.55	.39
	B	.96	.94	.85
	D	.59	.49	.24
15	(Boiling 3.5% NaCl at pH 1.5)			
	7	.92	.90	.92
	8	.92	.79	.85
20	9	.91	.89	.84
	10	.95	.90	.88
	11	.94	.88	.91
	B	.98	.92	.99
	D	.93	.70	.83
25	(Boiling 3.5% NaCl at pH 4.9-5.9)			
	7	.98	.94	1.0
	8	.98	.98	1.0
30	9	.98	.95	.93
	10	.97	1.0	.92
	11	1.0	.98	1.0
	B	.96	.90	.96
	D	.95	.77	.92
35	⁽¹⁾ TC/TR = Average time-to-fracture under corrosive conditions divided by average time-to-fracture under reference conditions.			
40	⁽²⁾ EC/ER = Average elongation under corrosive conditions divided by average elongation under reference conditions.			
45	⁽³⁾ RC/RR = Average reduction in area under corrosive conditions divided by average reduction in area under reference conditions.			

The mechanical properties of Examples 7-11 and Heats B and D were also determined and are presented in Table 7 including the 0.2% offset yield strength (.2% YS) and the ultimate tensile strength (UTS) in ksi (MPa), the percent elongation in four diameters (%)

Elong.), the reduction in area (% Red. in Area), and the notch tensile strength (NTS) in ksi (MPa).

Table 7

Ex./Ht. No.	Condition	.2% YS (ksi/MPa)	UTS (ksi/MPa)	% Elong.	% Red. in Area	NTS (ksi/MPa)
7	H1000	216.8/1495	230.5/1589	15.0	62.5	344.6/2376
8	H1000	223.0/1538	233.6/1611	14.5	64.0	353.0/2434
9	H1000	223.4/1540	234.8/1619	14.8	64.3	349.6/2410
10	H1000	219.3/1512	230.0/1586	14.4	65.0	348.6/2404
11	H1000	210.5/1451	230.9/1592	15.0	63.0	344.2/2373
B	H1050	184.1/1269	190.8/1316	17.9	72.3	303.4/2092
D	H1050	182.9/1261	196.9/1358	17.6	62.1	296.3/2043

When considered together, the data presented in Tables 6 and 7 demonstrate the unique combination of strength and stress corrosion cracking resistance provided by the alloy according to the present invention, as represented by Examples 7-11. More particularly, the data in Tables 6 and 7 show that Examples 7-11 are capable of providing significantly higher strength than comparative Heats B and D, while providing a level of stress corrosion cracking resistance that is comparable to those alloys. Additional specimens of Examples 7 and 11 were age hardened at 1050°F (538°C) for 4 hours and then air-cooled. Those specimens provided room temperature ultimate tensile strengths of 214.3 ksi and 213.1 ksi, respectively, which are still significantly better than the strength provided by Heats B and D when similarly aged. Although not tested, it would be expected that the stress corrosion cracking resistance of Examples 7 and 11 would be at least the same or better when aged at the higher temperature. In addition, it should be noted that the boiling 10.0% NaCl conditions are more severe than recognized standards for the aircraft industry.

The terms and expressions that have been employed herein are used as terms of description and not of limitation. There is no intention in the use of such terms and expressions to exclude any equivalents of

- 20 -

the features described or any portions thereof. It is recognized, however, that various modifications are possible within the scope of the invention claimed.

- 21 -

What is claimed is:

1. A precipitation hardenable, martensitic stainless steel alloy having a unique combination of stress-corrosion cracking resistance, strength, and notch toughness consisting essentially of, in weight percent, about

	C	0.03 max
	Mn	1.0 max
	Si	0.75 max
10	P	0.040 max
	S	0.020 max
	Cr	10 - 13
	Ni	10.5 - 11.6
	Ti	1.5 - 1.8
15	Mo	0.25 - 1.5
	Cu	0.95 max
	Al	0.25 max
	Nb	0.3 max
	B	0.010 max
20	N	0.030 max

the balance essentially iron.

2. The alloy recited in Claim 1 which contains no more than about 0.75 weight percent copper.

25

3. The alloy recited in Claim 1 which contains no more than about 0.10 weight percent aluminum.

4. The alloy recited in Claim 1 which contains no more than about 0.10 weight percent niobium.

30

5. The alloy recited in Claim 1 which contains no more than about 11.25 weight percent nickel.

6. The alloy recited in Claim 1 which contains at least about 10.75 weight percent nickel.

35

7. The alloy recited in Claim 1 which contains at least about 10.5 weight percent chromium.

40

- 22 -

8. The alloy recited in Claim 1 which contains no more than about 12.5 weight percent chromium.
9. The alloy recited in Claim 1 which contains no more than about 1.7 weight percent titanium.
10. The alloy recited in Claim 1 which contains no more than about 1.25 weight percent molybdenum.
11. The alloy recited in Claim 1 which contains at least about 0.75 weight percent molybdenum.
12. A precipitation hardenable, martensitic stainless steel alloy having a good combination of stress-corrosion cracking resistance, strength, and notch toughness consisting essentially of, in weight percent, about
- | | |
|----|---------------|
| C | 0.02 max |
| Mn | 0.25 max |
| Si | 0.25 max |
| P | 0.015 max |
| S | 0.010 max |
| Cr | 10.5 - 12.5 |
| Ni | 10.75 - 11.25 |
| Ti | 1.5 - 1.7 |
| Mo | 0.75 - 1.25 |
| Cu | 0.50 max |
| Al | 0.050 max |
| Nb | 0.050 max |
| B | 0.001 - 0.005 |
| N | 0.015 max |
- the balance essentially iron.
13. The alloy recited in Claim 12 which contains no more than about 12.0 weight percent chromium.
14. The alloy recited in Claim 12 which contains at least about 11.0 weight percent chromium.
15. The alloy recited in Claim 12 which contains at least about 10.85 weight percent nickel.

- 23 -

16. The alloy recited in Claim 12 which contains no more than about 1.1 weight percent molybdenum.

17. The alloy recited in Claim 12 which contains
5 at least about 0.9 weight percent molybdenum.

18. A precipitation hardenable, martensitic stainless steel alloy having a good combination of stress-corrosion cracking resistance, strength, and
10 notch toughness consisting essentially of, in weight percent, about

	C	0.015 max
	Mn	0.10 max
	Si	0.10 max
15	P	0.010 max
	S	0.005 max
	Cr	11.0 - 12.0
	Ni	10.85 - 11.25
	Ti	1.5 - 1.7
20	Mo	0.9 - 1.1
	Cu	0.25 max
	Al	0.025 max
	Nb	0.025 max
	B	0.0015 - 0.0035
25	N	0.010 max

the balance essentially iron.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/14214

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C22C38/44 C22C38/50

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C22C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,93 07303 (SANDVIK A.B.) 15 April 1993 see claims 1-5	1-18
A	--- EP,A,0 604 062 (ETHICON INC.) 29 June 1994 see claims 1-13	1-18
A	--- SU,A,395 489 (GELLER ET AL.) 22 January 1974 see the whole document	1-18
A	--- PATENT ABSTRACTS OF JAPAN vol. 12, no. 405 (C-539), 26 October 1988 & JP,A,63 145751 (KAWASAKI STEEL CORP.), 17 June 1988, see abstract -----	1-18

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

a document member of the same patent family

Date of the actual completion of the international search

19 November 1996

Date of mailing of the international search report

28. 11. 96

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Lippens, M

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/14214

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9307303	15-04-93	SE-B- 469986	18-10-93
		AU-B- 669675	20-06-96
		AU-A- 2775592	03-05-93
		BR-A- 9206594	28-11-95
		CA-A- 2119150	15-04-93
		CZ-A- 9400815	16-08-95
		EP-A- 0607263	27-07-94
		FI-A- 941581	06-04-94
		HU-A- 66819	30-01-95
		JP-T- 6511287	15-12-94
		NO-A- 941236	06-04-94
		PT-A- 100934	30-06-94
		SE-A- 9102889	08-04-93
		US-A- 5512237	30-04-96
		ZA-A- 9207532	25-05-93

EP-A-604062	29-06-94	AU-B- 664928	07-12-95
		AU-A- 5203893	23-06-94
		BR-A- 9304977	28-06-94
		CA-A- 2110928	10-06-94
		GR-A- 93100464	31-08-94
		JP-A- 7070703	14-03-95

SU-A-395489		NONE	
